

PARFIX WOOD D4

VODOOTPORNI LEPAK ZA DRVO KLASSE D4 / ONE-COMPONENT WATERPROOF ADHESIVE
CLASS D4 FOR WOOD / ВОДОСТОЙКИЙ КЛЕЙ ДЛЯ ДРЕВЕСИНЫ КЛАССА D4



Product benefits



OPIS PROIZVODA I UPOTREBA

Dvokomponentni vodootporni lepak za drvo klase D4(EN 204), na bazi modifikovane polivinilacetatne vodene disperzije. Posebnost lepka, pored vodootpornosti, je i visoka čvrstoća vezivanja tvrdog i mekog drveta. Koristi se za bilo koju vrstu lepljenja drveta. Nakon sušenja lepak je transparentan otporan na vlagu i plesni.

- EKOLOŠKI PROIZVOD
- VOC FREE
- OTPORNO NA VODU I VLAGU
- OTPORNO NA VISOKE TEMPERATURE
- VISOKA ČVRSTOĆA VEZIVANJA TVRDOG I MEKOG DRVETA

INFORMACIJE O PROIZVODU:

Boja proizvoda: bezbojan

Način rada: površina za lepljenje treba da bude glatka, suva, bez prašine i masnoća. U posudu sa komponentom A, treba ubaciti sadržaj komponente B. Sadržaj promešati pomoću električnog miksera, nikako ručno. Nanosi se ravnomerno, ručno-četkom ili mašinski (valjcima, diskovima)

Potrošnja: cca.150-180g/m²

Uslovi lepljenja: pritisak presovanja je 0.5-1.0 N /mm²

Vreme presovanja: 120 min (može biti i kraće vreme u zavisnosti od veličine, vrste elementa i vrste drveta)

Temperatura primene: najpovoljnija temperatura lepka, drveta i okoline za obradu je +15°C do + 20°C, vlažnost vazduha 60%; najpovoljnija vlažnost drveta 8 – 12%. Ne sme se lepiti na temperaturi nižoj od +11°C

Otvoreno vreme rada: 6-10 min

Vreme sušenja: 24h u posudi sa očvršćivačem


Preporučena upotreba: enterijer i eksterijer

Pogodno za: koristi se za bilo koju vrstu lepljenja drveta; lepak je namenjen i za lepljenje masivnih obloga, ivica od plastike i šperploče; koristi se i za lepljenje drveta drugim materijalima npr. plutom, tekstilom, kožom itd. Takođe koristi se i za lepljenje prozora, greda prozora i spoljnih vrata

Skладиštenje: čuvati u originalnoj dobro zatvorenoj i neoštećenoj ambalaži, pri temperaturi od +5°C do + 25°C, zaštićeno od direktne sunčeve svetlosti

Napomena: čuvati od smrzavanja i pregrevanja

Pakovanje: komponenta A i komponenta B (komponenta B se nalazi u plastičnoj kanti sa komponentom A); 20kg+1kg



ENG

PROPERTIES AND PURPOSE:

Parfix Wood D4 is two-component waterproof adhesive class D4 (EN204) for wood, based on the modified polyvinyl acetate water dispersion. A special feature of the adhesive, besides its water resistance, is a high bonding strength of the hard and soft wood. It is used for any kind of wood bonding. After drying, the adhesive is transparent, resistant to the moisture and mold.

- ECOLOGICAL PRODUCT
- VOC FREE · WATER RESISTANT
- MOISTURE RESISTANT
- HIGH TEMPERATURES RESISTANT
- HIGH BONDING STRENGTH OF THE HARD AND SOFT WOOD

INFORMATIONS ABOUT PRODUCT:

Color of the product: colorless

Preparation and application: substrate on which adhesive is applied has to be smooth, clean, dry, degreased and dusted. Content from component B pour in bowl with component A. Both components mix well with slow-rotating mixer (using a drill - not by hand). Apply it evenly, manually – with paint brush or mechanical (with paint rollers, disks)

Consumption: approx. 150 – 180g/m²

Gluing conditions: pressing pressure: 0.5 – 1.0 N/mm²

Pressing time: 120min (time could be shorter, depending on dimensions, type of elements and type of wood)

Application temperature: optimal temperature of glue, wood and environment is +15°C – +20°C, air humidity 60%; optimal wood humidity 8 – 12%. The glue should not be used for gluing surfaces at air temperature lower than +11°C

Open working time: 6 – 10min

Drying time: 24h in bowl with hardener

Recommended use: interior and exterior

Suitable for: any kind of wood – gluing massive panels, edges made of plastics and plywood. Parfix Wood D4 glue is used also for the adhesion of the wood with other materials for example with cork, fabrique, leather, etc. It is used also for the adhesion of the windows, window beams and external doors

Storage: keep in original, well closed and undamaged packaging at temperature +5°C – +25°C, protected from direct sunlight

Note: keep safe from frost and overheating

Packaging: Component A and component B (comp. B is in plastic can with comp. A); 20kg + 1kg

RUS

ХАРАКТЕРИСТИКИ И НАЗНАЧЕНИЕ:

Двухкомпонентный водостойкий клей для древесины класса D4 (EN 204) на основе модифицированной поливинилацетатной водной дисперсии. Особенностью клея, помимо водостойкости, является высокая прочность склеивания твердой и мягкой древесины. Используется для склеивания любых видов древесины. После высыхания клей становится прозрачным, устойчивым к влаге и плесени.

- ЭКОЛОГИЧЕСКИЙ ПРОДУКТ
- VOC FREE
- ВОДОНЕПРОНИЦАЕМЫЙ
- ВЛАГОУСТОЙЧИВЫЙ
- УСТОЙЧИВОСТЬ К ВЫСОКИМ ТЕМПЕРАТУРАМ
- ВЫСОКАЯ ПРОЧНОСТЬ СКЛЕИВАНИЯ ТВЕРДОЙ И МЯГКОЙ ДРЕВЕСИНЫ

ИНФОРМАЦИЯ О ПРОДУКТЕ:

Цвет продукта: бесцветный

Способ применения: склеиваемая поверхность должна быть гладкой, сухой, очищенной от пыли и жира. В емкость с компонентом А необходимо поместить содержимое компонента В. Перемешать содержимое электрическим миксером, ни в коем случае не вручную. Наносится равномерно, вручную с помощью кисти или машинным способом (валики, диски).

Расход: прикл. 150-180 г/м²

Условия склеивания: давление прессования 0,5-1,0 Н / мм²

Время прессования: 120 мин (может быть короче в зависимости от размера, типа элемента и породы древесины)

Температура применения: наиболее благоприятная температура для клея, древесины и окружающей среды для обработки - от +15°C до +20°C, влажность воздуха - 60%; наиболее благоприятная влажность древесины - 8 - 12%. Не допускается склеивание при температуре ниже +11°C

Время работы: 6-10 мин

Время высыхания: 24 ч в контейнере с отвердителем

Рекомендуемое применение: интерьер и экстерьер

Подходит для: используется для любого вида склеивания древесины; клей также предназначен для склеивания массивных покрытий, пластиковых кромок и фанеры; используется для склеивания древесины с другими материалами, например, пробкой, текстилем, кожей и т.д. Он также используется для склеивания окон, оконных балок и наружных дверей.

Хранение: хранить в оригинальной хорошо закрытой и неповрежденной упаковке, при температуре от +5°C до + 25°C, в защищенном от прямых солнечных лучей месте.

Примечание: беречь от замерзания и перегрева

Упаковка: компонент А и компонент В (компонент В находится в пластиковом ведре с компонентом А); 20 кг + 1 кг